

GW 3009-H NATURAL LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore D Hardness	66	-	ASTM D 2240
Tensile Strength	16.5	MPa	ASTM D 412
Elongation at Break	250	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	44	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1580	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe