

GW 3025-VW1 NAT LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	95	-	ASTM D 2240
Tensile Strength	15.2	MPa	ASTM D 412
Elongation at Break	280	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	37	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1480	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe