

GW 3044 NATURAL LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	96	-	ASTM D 2240
Tensile Strength	15.2	MPa	ASTM D 412
Elongation at Break	290	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	41	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1530	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Special Characteristics

Flame retardant

Applications

Electrical and Electronical

Regional Availability

North America, Europe