

GW 3280-F3 NATURAL LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore D Hardness	63	-	ASTM D 2240
Tensile Strength	16.5	MPa	ASTM D 412
Elongation at Break	260	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	40	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1540	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe