

GW 8106 NATURAL LCF

PVC

Alphagary

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Shore D Hardness | 71 | - | ASTM D 2240 |
| Tensile Strength | 19.3 | MPa | ASTM D 412 |
| Elongation at Break | 290 | % | ASTM D 412 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Limiting Oxygen Index | 39 | % | ASTM D 2863 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1510 | kg/m ³ | ASTM D 792 |

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe