

GWX 88-366-EC4 NAT LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	96	-	ASTM D 2240
Tensile Strength	15.9	MPa	ASTM D 412
Elongation at Break	320	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	42	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1490	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe