

GWX 90-670-D NAT UV-LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore D Hardness	60	-	ASTM D 2240
Tensile Strength	20	MPa	ASTM D 412
Elongation at Break	330	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	31	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dissipation Factor, 1 MHz	0.015	-	ASTM D 150
Dielectric Constant, 1 MHz	2.9	-	ASTM D 150

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Applications

Electrical and Electronical

Special Characteristics

Flame retardant, U.V. stabilized or stable to weather

Regional Availability

North America, Europe