

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>3100</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>51.7</b>	MPa	ASTM D 638
Flexural Modulus	<b>2760</b>	MPa	ASTM D 790
Flexural Strength	<b>82.7</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>64</b>	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	<b>1360</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Film Extrusion

#### Delivery form

Pellets

#### Special Characteristics

U.V. stabilized or stable to weather, Transparent

#### Applications

General Purpose

#### Regional Availability

North America