

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[S]</sup></b>			
Tensile Strength	<b>9</b>	MPa	GOST 11262
Strain at break	<b>356</b>	%	GOST 11262
Shore A hardness	<b>77</b>	-	GOST 263

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[S]</sup></b>			
Volume resistivity	<b>1E8</b>	Ohm*m	GOST 6433.2

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[S]</sup></b>			
Density	<b>1230</b>	kg/m <sup>3</sup>	GOST 15139

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Regional Availability

Europe