

Vynaprene 7907

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1538	MPa	ASTM D 638
Tensile Strength at Yield	27.1	MPa	ASTM D 638
Flexural Modulus	551	MPa	ASTM D 790
Flexural Strength	40.9	MPa	ASTM D 790
Rockwell Hardness	R 90	-	ASTM D 785
Shore D Hardness	73.8	-	ASTM D 2240
Izod Impact notched, 1/8 in	1270	J/m	ASTM D 256
Izod Impact notched, 1/4 in	1110	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America