

## Kynar Flex® PPA 2200

PVDF

ARKEMA

### Product Texts

**Kynar Flex® resins** are fluorinated thermoplastic copolymers.

**Kynar Flex® PPA 2200 resin** is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of **Kynar Flex® PPA 2200 resin** at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>144</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>700</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

### Characteristics

#### Processing

Film Extrusion, Sheet Extrusion, Other Extrusion

#### Features

Copolymer

#### Delivery form

Granules, Powder

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa