

**Product Texts**

**Kynar Flex® resins** are fluorinated thermoplastic copolymers.

**Kynar Flex® PPA 5300 resin** is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of **Kynar Flex® PPA 5300 resin** at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as **Kynar Flex® PPA 5301 resin**.

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>165</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>700</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Film Extrusion, Sheet Extrusion, Other Extrusion

**Features**

Copolymer

**Delivery form**

Granules, Powder

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa