

Product Texts

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® PPA 8600 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of **Kynar Flex® PPA 8600 resin** at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as **Kynar Flex® PPA 8601 resin**.

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	700	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Film Extrusion, Sheet Extrusion, Other Extrusion

Features

Copolymer

Delivery form

Granules, Powder

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa