

Dryflex® AM 55A201B

SB

Hexpol TPE

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	2.2	MPa	ISO 37
Tear strength	16	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	20 - 60	°C	-
Feed temperature	170 - 190	°C	-
Zone 1	180 - 200	°C	-
Zone 2	190 - 210	°C	-
Zone 3	200 - 210	°C	-

Characteristics**Processing**

Injection Molding

Features

Anti Slip, Low Fogging, Low Odor, Scratch Resistant

Chemical Resistance

General Chemical Resistance, Solvent Resistance, Oil Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific