

HIPREN® EM 1712 T TDAE

SBR

HIP-Petrohemija

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 300% elongation	41.1	MPa	ISO 527
Stress at break TPE	19	MPa	ISO 527
Strain at break TPE	>300	%	ISO 527
Shore A hardness	64	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	410	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183

Characteristics**Delivery form**

Brown

Applications

General Purpose

Features

Copolymer

Regional Availability

Europe