

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Shore A hardness	70	-	ISO 7619-1
<b>Other Standards<sup>[S]</sup></b>			
Tensile Strength	6.5	MPa	DIN 53504
Strain at break TPE	850	%	DIN 53504

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1180	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	190 - 220	°C	-

## Characteristics

### Processing

Other Extrusion

### Special Characteristics

U.V. stabilized or stable to weather

### Features

Good Adhesion, Melt Strength

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa