

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Shore A hardness	80	-	ISO 7619-1
Other Standards^[5]			
Tensile Strength	4	MPa	DIN 53504
Strain at break TPE	100	%	DIN 53504

S: These properties are reported by the producer according standards that are different to our defaults.

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	10000	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 70	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.1	%	-
Melt temperature	190 - 220	°C	-
Mold temperature	20 - 40	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Increased electrical conductivity

Features

Good Adhesion

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa