

Dryflex® AM 50A204B

SEBS

Hexpol TPE

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	4	MPa	ISO 37
Tear strength	20	kN/m	ISO 34-1
Abrasion resistance	340	mm ³	ISO 4649

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	20 - 60	°C	-
Feed temperature	170 - 210	°C	-
Zone 1	180 - 220	°C	-
Zone 2	190 - 230	°C	-
Zone 3	200 - 240	°C	-

Characteristics**Processing**

Injection Molding

Chemical Resistance

General Chemical Resistance, Solvent Resistance

Special Characteristics

U.V. stabilized or stable to weather

Applications

Automotive

Features

Anti Slip, Low Fogging, Low Odor, Scratch Resistant

Regional Availability

North America, Europe, Asia Pacific