

**HX700**

SMMA

LX MMA Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000	MPa	ISO 527
Stress at break	65	MPa	ISO 527
Strain at break	5.2	%	ISO 527
Flexural modulus, 23°C	3200	MPa	ISO 178
Flexural strength	105	MPa	ISO 178
Charpy notched impact strength, +23°C	1.4	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	M 84	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, B	105	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	60	E-6/K	ASTM D 696

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Haze	0.5	-	ISO 14782
Luminous transmittance	91	%	ISO 13468-1, -2
<b>Other Standards<sup>[5]</sup></b>			
Index of Refraction	1.53	-	ISO 489

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1150	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.18	%	ASTM D 570

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	210 - 240	°C	-
Mold temperature	50 - 70	°C	-

**Characteristics****Processing**

Other Extrusion

**Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Light Guiding, Copolymer

**Certifications**

Food contact

**Applications**

Electrical and Electronical, Packaging

**Regional Availability**

North America, Europe, Asia Pacific