

MS-200 NT

SMMA

Toyo Styrene Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	58	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	3420	MPa	ISO 178
Flexural strength	110	MPa	ISO 178
Charpy notched impact strength, +23°C	2.2	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	79	°C	ISO 75-1/-2
Vicat softening temperature, B	99	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow Card available	yes	-	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	0.1	%	ASTM D 1003
Light Transmittance	90	%	ASTM D 1003
Other Standards^[S]			
Index of Refraction	1.57	-	ISO 489

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1070	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Regional Availability

Asia Pacific