

**Product Texts**

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

**Hytrel® 8238 is the highest modulus grade, with nominal hardness of 82D. It contains non-discoloring stabilizer. It can be processed by many conventional thermoplastic processing techniques like injection molding and extrusion.**

Typical applications:

Cubing, wire and cable, gears, sprockets, electrical connectors and oil field parts.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	11.5	cm <sup>3</sup> /10min	ISO 1133
Temperature	240	°C	-
Load	2.16	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1130	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.15	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2150	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	5.44E-8	m <sup>2</sup> /s	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	12.5	g/10min	ASTM D 1238
Temperature	240	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	1200	MPa	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Tensile notched impact strength, +23°C	57	kJ/m <sup>2</sup>	ISO 8256/1
<sup>[C]</sup> Stress at 10% elongation	34	MPa	ISO 527
<sup>[C]</sup> Stress at 100% elongation	26	MPa	ISO 527
<sup>[C]</sup> Stress at break TPE	46	MPa	ISO 527
<sup>[C]</sup> Strain at break TPE	>300	%	ISO 527
<sup>[C]</sup> Shore D hardness	70	-	ISO 7619-1
<b>ASTM Data</b>			
Tensile Strength at Break	48.3	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Flexural Modulus	1110	MPa	ASTM D 790
Shore D Hardness	82	-	ASTM D 2240
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	30	J/m	ASTM D 256
Temperature	-40	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	45	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	105	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	150	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	150	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	140	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.9	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Oxygen index	22	%	ISO 4589-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Coefficient of Thermal Expansion, MD	149	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	147	E-6/K	ASTM D 696
DTUL @ 66 psi	140	°C	ASTM D 648
DTUL @ 264 psi	55	°C	ASTM D 648
Melting Temperature	223	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	4	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.7	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	100	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	175	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	21	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.6	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.2	%	Sim. to ISO 62
<sup>[C]</sup> Density	1280	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.3	%	ASTM D 570
Density	1280	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion, Coating, Casting, Thermoforming

**Delivery form**

Pellets

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Automotive

**Additives**

Release agent

**Special Characteristics**

Platable, Light stabilized or stable to light, Heat stabilized or stable to heat

**Features**

Color Stability, Creep Resistance, Weldable

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa