

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® 8238HS is the highest modulus grade, with nominal hardness of 82D. It contains non-discoloring stabilizer. It can be processed by many conventional thermoplastic processing techniques like injection molding and extrusion.

Typical applications:

Cubing, wire and cable, gears, sprockets, electrical connectors and oil field parts.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.4	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1050	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	5.5	kJ/m ²	ISO 179/1eA
^[C] Stress at 10% elongation	36	MPa	ISO 527
^[C] Stress at break TPE	49	MPa	ISO 527
^[C] Strain at break TPE	290	%	ISO 527
^[C] Shore D hardness	70	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Glass transition temperature, 10°C/min	45	°C	ISO 11357-1/-2

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Casting, Thermoforming

Delivery form

Pellets

Special Characteristics

Light stabilized or stable to light, Heat stabilized or stable to heat

Features

Color Stability

Regional Availability

North America, Europe, Asia Pacific, South and Central America