

**Product Texts**

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

**Hytrel® ECO 4056B is a low modulus Hytrel® grade with nominal durometer hardness of 40D and with high impact resistance down to -40°C. It contains a non-discoloring stabilizer. It is recommended for extrusion and compounding. It has same performance and processing properties as Hytrel® 4056.**

Hytrel® ECO 4056B belongs to the Hytrel® ECO B family. The products of this family are partially produced using bio-feedstock derived from waste\*. This results in reduced lifecycle greenhouse gas emissions and lower fossil resource use.

\*certified bio-circular according to ISCC Plus mass balance approach.

Typical applications:

Hose and tubing, hose jackets, wire and cable jackets, film and sheeting, belting and seals, .

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>5</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	<b>0.2</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>0.4</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	<b>1020</b>	kg/m <sup>3</sup>	-
<sup>[C]</sup> Eff. thermal diffusivity	<b>8.5E-8</b>	m <sup>2</sup> /s	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>60</b>	MPa	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	<b>54</b>	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	<b>40</b>	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Tensile notched impact strength, +23°C	<b>230</b>	kJ/m <sup>2</sup>	ISO 8256/1
<sup>[C]</sup> Puncture - maximum force, +23°C	<b>1500</b>	N	ISO 6603-2
<sup>[C]</sup> Puncture - maximum force, -30°C	<b>2800</b>	N	ISO 6603-2
<sup>[C]</sup> Puncture energy, +23°C	<b>19</b>	J	ISO 6603-2
<sup>[C]</sup> Puncture energy, -30°C	<b>37</b>	J	ISO 6603-2
<sup>[C]</sup> Stress at 10% elongation	<b>4.6</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break TPE	<b>22</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break TPE	<b>&gt;300</b>	%	ISO 527
<sup>[C]</sup> Abrasion resistance	<b>200</b>	mm <sup>3</sup>	ISO 4649
<sup>[C]</sup> Shore D hardness	<b>37</b>	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	152	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	-50	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	48	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	160	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Oxygen index	20	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	5.2	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	4.7	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	110	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	525	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	7E10	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	2E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	18	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.7	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.2	%	Sim. to ISO 62
<sup>[C]</sup> Density	1160	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Film Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> WVTR, 23°C/85%r.h.	450	g/(m <sup>2</sup> *d)	ISO 15106-1/-2
<sup>[C]</sup> Oxygen transmission rate, 23°C/85%r.h.	14000	cm <sup>3</sup> /(m <sup>2</sup> *d*bar)	ISO 15105-1/-2
<sup>[C]</sup> Thickness of specimen	0.025	mm	-

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Coating, Calendering, Casting, Thermoforming

### Delivery form

Pellets

### Special Characteristics

Light stabilized or stable to light

### Certifications

Contains renewable resources, ISCC Plus

## Other text information

### Injection molding

Snake Flow Test , mm

Inject press 62MPa, 1mm                      80

Created: 11.03.2026 Source: www.materialdatacenter.com

Page: 2/2

Copyright © 2026 Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the terms of the license agreement. Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

Inject press 83MPa(12,000psi),              430  
2.5mm