

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow moulding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticizer free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® G4078LS NC010 is a low modulus grade with nominal hardness of 40D. It contains non-discoloring stabilizer. It can be processed with many conventional thermoplastic processing techniques like injection molding and extrusion.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Stress at 10% elongation	4.2	MPa	ISO 527
^[C] Stress at break TPE	21	MPa	ISO 527
^[C] Strain at break TPE	>300	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	-45	°C	ISO 11357-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	6.8	%	Sim. to ISO 62
^[C] Humidity absorption	0.7	%	Sim. to ISO 62
^[C] Density	1180	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Casting, Thermoforming

Delivery form

Pellets, Natural Color

Special Characteristics

Light stabilized or stable to light

Features

Color Stability

Regional Availability

North America, Europe, Asia Pacific, South and Central America