

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® HTR8223 BK320 is designed for blow molding or processing techniques requiring high melt viscosity. It has nominal hardness of 42D.

Typical applications:

Constant velocity joint boots.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	10	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	10	kg	-
^[C] Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
^[C] Density of melt	980	kg/m ³	-
^[C] Eff. thermal diffusivity	5.44E-8	m ² /s	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 10% elongation	5.5	MPa	ISO 527
^[C] Stress at 100% elongation	13	MPa	ISO 527
^[C] Stress at 300% elongation	19	MPa	ISO 527
^[C] Stress at break TPE	26	MPa	ISO 527
^[C] Strain at break TPE	>300	%	ISO 527
^[C] Abrasion resistance	22	mm ³	ISO 4649
^[C] Shore D hardness	36	-	ISO 7619-1
ASTM Data			
Shore D Hardness	45	-	ASTM D 2240

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	195	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	-50	°C	ISO 11357-1/-2
^[C] Coeff. of linear therm. expansion, parallel	170	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	170	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Dissipation factor, 100Hz	70	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	125	E-4	IEC 62631-2-1
^[C] Volume resistivity	9E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	2E14	Ohm	IEC 62631-3-2

Hytrell® HTR8223 BK320

TPC

Celanese

[C] Electric strength	18	kV/mm	IEC 60243-1
[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Water absorption	0.8	%	Sim. to ISO 62
[C] Humidity absorption	0.2	%	Sim. to ISO 62
[C] Density	1130	kg/m ³	ISO 1183
Water Absorption, 24hr	0.6	%	ASTM D 570

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion, Coating, Blow Molding, Casting, Thermoforming

Delivery form

Pellets, Black

Additives

Release agent

Special Characteristics

Platable, Light stabilized or stable to light, Heat stabilized or stable to heat

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa