

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.
Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.
For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® SC956 NC010 is a medium modulus grade with nominal hardness of 55D, contains a non-discoloring stabilizer and processed by many conventional thermoplastic processing techniques. Developed for applications such as parts for the healthcare industry.

SPECIAL CONTROL for HEALTHCARE APPLICATIONS

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in the USA when meeting applicable use conditions. This product is also tested against ISO 10993-5 and -11 and selected parts of USP Class VI. For details, individual compliance statements are available from our representative.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.4	%	ISO 294-4, 2577
^[C] Density of melt	1030	kg/m ³	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	180	MPa	ISO 527
^[C] Tensile creep modulus, 1h	170	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	130	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	150	kJ/m ²	ISO 179/1eA
^[C] Tensile notched impact strength, +23°C	300	kJ/m ²	ISO 8256/1
^[C] Stress at 10% elongation	11	MPa	ISO 527
^[C] Stress at 100% elongation	16	MPa	ISO 527
^[C] Stress at break TPE	40	MPa	ISO 527
^[C] Strain at break TPE	>300	%	ISO 527
^[C] Abrasion resistance	120	mm ³	ISO 4649
^[C] Shore D hardness	51	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	201	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	-20	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	75	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	180	E-6/K	ISO 11359-1/-2

Hytre® SC956 NC010

TPC

Celanese

[C] Coeff. of linear therm. expansion, normal	180	E-6/K	ISO 11359-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Water absorption	0.6	%	Sim. to ISO 62
[C] Humidity absorption	0.2	%	Sim. to ISO 62
[C] Density	1190	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Coating, Transfer Molding, Casting, Thermoforming

Delivery form

Pellets, Natural Color

Special Characteristics

Light stabilized or stable to light

Features

Color Stability

Regional Availability

North America, Europe, Asia Pacific, South and Central America