

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	25	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	N	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	35	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	195	°C	ISO 11357-1/-3
^[C] Oxygen index	20	%	ISO 4589-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.9	%	Sim. to ISO 62
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa