

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Shore D hardness	<b>41</b>	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>200</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Oxygen index	<b>20</b>	%	ISO 4589-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Humidity absorption	<b>0.6</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1140</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding, Blow Molding

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa