

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	549	MPa	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	17.8	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6.8	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	68	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	218	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1270	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa