

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	42	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	N	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	41	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	200	°C	ISO 11357-1/-3
^[C] Oxygen index	20	%	ISO 4589-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.6	%	Sim. to ISO 62
^[C] Density	1140	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Other Extrusion, Blow Molding

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa