

PIBIFLEX® L6060

TPC

Celanese

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|---|-------------|------------------------|---------------|
| ISO Data | | | |
| ^[C] Melt volume-flow rate, MVR | 74 | cm ³ /10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

[C]: CAMPUS

| Mechanical properties | Value | Unit | Test Standard |
|--|-----------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Charpy notched impact strength, +23°C | N | kJ/m ² | ISO 179/1eA |
| ^[C] Charpy notched impact strength, -30°C | N | kJ/m ² | ISO 179/1eA |
| ^[C] Shore D hardness | 55 | - | ISO 7619-1 |

[C]: CAMPUS

| Thermal properties | Value | Unit | Test Standard |
|--|------------|------|----------------|
| ISO Data | | | |
| ^[C] Melting temperature, 10°C/min | 216 | °C | ISO 11357-1/-3 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------|-------------|-------------------|---------------|
| ^[C] Density | 1220 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa