

3235

TPE

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.0165	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	6.2	MPa	ASTM D 638
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Other properties			
Density	880	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific