

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>30</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Shore A Hardness	<b>40</b>	-	ASTM D 2240
Tensile Strength	<b>6.21</b>	MPa	ASTM D 412
Elongation at Break	<b>500</b>	%	ASTM D 412

<b>Other Standards<sup>[5]</sup></b>			
Tensile Modulus	<b>1.241</b>	MPa	ASTM D 412

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1030</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Regional Availability**

North America