

AlphaSeal® 225

TPE

Alphagary

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10.8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	8.27	MPa	ASTM D 638
Elongation at Break	450	%	ASTM D 638
Shore A Hardness	95	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	930	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America, Europe