

AlphaSeal® 240-6CY BLUE 7002

TPE

Alphagary

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	13.4	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Shore A Hardness	95	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	930	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Certifications

Food contact, Food approval FDA 21 CFR

Features

Low Odor

Regional Availability

North America, Europe