

**APINAT™ DP2150**

TPE

Grade is obsolete.

Trinseo

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>19.8</b>	MPa	ASTM D 638
Elongation at Break	<b>46</b>	%	ASTM D 638
Flexural Modulus	<b>835</b>	MPa	ASTM D 790
Shore D Hardness	<b>61</b>	-	ASTM D 2240
Tear Strength	<b>85</b>	kN/m	ASTM D 624
<b>Other properties</b>			
Density	<b>1220</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets

**Certifications**

Contains renewable resources, Biodegradable, Compostable ISO 13432 (Producer), Compostable ASTM D6400 (Producer)

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa