

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at 100% elongation	<b>1.3</b>	MPa	ISO 527
Stress at 300% elongation	<b>2.6</b>	MPa	ISO 527
Tensile Strength	<b>4</b>	MPa	ISO 37
Strain at break	<b>600</b>	%	ISO 37
Compression set at 70 °C, 24h	<b>43</b>	%	ISO 815
Tear strength	<b>24</b>	kN/m	ISO 34-1
Shore A hardness	<b>50</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>980</b>	kg/m <sup>3</sup>	ISO 1183
Biobased content	<b>82</b>	%	-

**Characteristics**

**Features**

Good Adhesion, Soft Feel

**Certifications**

Contains renewable resources

**Applications**

Automotive, Sports Equipment

**Regional Availability**

North America, Europe, Asia Pacific