

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at 100% elongation	<b>2.8</b>	MPa	ISO 527
Stress at 300% elongation	<b>3.5</b>	MPa	ISO 527
Tensile Strength	<b>3.8</b>	MPa	ISO 37
Strain at break	<b>350</b>	%	ISO 37
Compression set at 70 °C, 24h	<b>66</b>	%	ISO 815
Tear strength	<b>27</b>	kN/m	ISO 34-1
Shore A hardness	<b>70</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>890</b>	kg/m <sup>3</sup>	ISO 1183
Biobased content	<b>63</b>	%	-

**Characteristics**

**Features**  
Good Adhesion, Soft Feel

**Applications**  
Automotive, Sports Equipment

**Certifications**  
Contains renewable resources

**Regional Availability**  
North America, Europe, Asia Pacific