

Dryflex® PCW 92A331B

TPE

Hexpol TPE

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 7.5 | MPa | ISO 37 |
| Strain at break | 450 | % | ISO 37 |
| Tear strength | 58 | kN/m | ISO 34-1 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1110 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Mold temperature | 20 - 60 | °C | - |
| Feed temperature | 170 - 190 | °C | - |
| Zone 1 | 180 - 200 | °C | - |
| Zone 2 | 190 - 210 | °C | - |
| Zone 3 | 200 - 220 | °C | - |

Characteristics**Processing**

Injection Molding

Certifications

Recycled Resin Content

Special Characteristics

U.V. stabilized or stable to weather

Applications

Automotive

Features

Acoustical Barrier Properties

Regional Availability

North America, Europe, Asia Pacific