

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 300% Elongation	0.85	MPa	ASTM D 412
Shore A Hardness	43	-	ASTM D 2240
Tensile Strength at Break	5.36	MPa	ASTM D 412
Elongation at Break	640	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	15.6 - 37.8	°C	-
Zone 1	149 - 188	°C	-
Zone 2	182 - 193	°C	-
Zone 3	188 - 227	°C	-
Nozzle temperature	188 - 227	°C	-
Screw speed	25 - 75	rpm	-
Injection speed	25.4 - 127	mm/s	-
Back pressure	0 - 0.827	MPa	-
Holding pressure	0.827 - 2.07	MPa	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Features

Good Adhesion, Soft Feel

Chemical Resistance

Ozone Resistance

Regional Availability

Asia Pacific