

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.03	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	0.393	MPa	ASTM D 412
Modulus at 300% Elongation	0.216	MPa	ASTM D 412
Shore A Hardness	14	-	ASTM D 2240
Tear Strength	7.01	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	9	%	ASTM D 395
Tensile Strength at Break	1.54	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	880	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	15.6 - 26.7	°C	-
Zone 1	149 - 177	°C	-
Zone 2	177 - 188	°C	-
Zone 3	188 - 216	°C	-
Nozzle temperature	188 - 216	°C	-
Screw speed	50 - 150	rpm	-
Injection speed	25.4 - 76.2	mm/s	-
Back pressure	0 - 0.758	MPa	-
Holding pressure	0.31 - 1.45	MPa	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Features

Good Adhesion, Soft Feel

Chemical Resistance

Ozone Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa