

Dynaflex™ G7630-9 (Black)

TPE

Avient Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	31	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	0.689	MPa	ASTM D 412
Modulus at 300% Elongation	0.55	MPa	ASTM D 412
Shore A Hardness	29	-	ASTM D 2240
Tear Strength	14.9	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	13	%	ASTM D 395
Tensile Strength at Break	3.28	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	15.6 - 37.8	°C	-
Zone 1	160 - 188	°C	-
Zone 2	177 - 193	°C	-
Zone 3	188 - 210	°C	-
Nozzle temperature	188 - 216	°C	-
Screw speed	40 - 100	rpm	-
Injection speed	25.4 - 76.2	mm/s	-
Back pressure	0 - 0.827	MPa	-
Holding pressure	0.689 - 3.1	MPa	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets, Black

Features

Anti Slip, Good Adhesion, Soft Feel

Certifications

Food contact, Food approval FDA 21 CFR

Applications

General Purpose, Sports Equipment

Regional Availability

Asia Pacific