

**Dynaflex™ G7660-9 (Black)**

TPE

Avient Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 100% Elongation	2.14	MPa	ASTM D 412
Modulus at 300% Elongation	1.01	MPa	ASTM D 412
Shore A Hardness	60	-	ASTM D 2240
Tear Strength	26.3	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	17	%	ASTM D 395
Tensile Strength at Break	6.62	MPa	ASTM D 412
Elongation at Break	720	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1180	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	15.6 - 37.8	°C	-
Zone 1	160 - 177	°C	-
Zone 2	177 - 193	°C	-
Zone 3	188 - 221	°C	-
Nozzle temperature	193 - 227	°C	-
Screw speed	40 - 100	rpm	-
Injection speed	25.4 - 76.2	mm/s	-
Back pressure	0 - 1.03	MPa	-
Holding pressure	0.724 - 1.86	MPa	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets, Black

**Features**

Good Adhesion, Soft Feel

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

General Purpose, Sports Equipment

**Regional Availability**

Asia Pacific