

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Modulus at 100% Elongation	0.896	MPa	ASTM D 412
Modulus at 300% Elongation	0.46	MPa	ASTM D 412
Shore A Hardness	30	-	ASTM D 2240
Tear Strength	17.5	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	13	%	ASTM D 395
Tensile Strength at Break	3.31	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Other properties			
Density	1050	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Mold temperature	15.6 - 37.8	°C	-
Zone 1	160 - 188	°C	-
Zone 2	177 - 193	°C	-
Zone 3	188 - 210	°C	-
Nozzle temperature	188 - 216	°C	-
Screw speed	40 - 100	rpm	-
Injection speed	25.4 - 76.2	mm/s	-
Back pressure	0 - 0.827	MPa	-
Holding pressure	0.689 - 3.1	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Features

Anti Slip, Good Adhesion, Soft Feel

Certifications

Food contact, Food approval FDA 21 CFR

Applications

General Purpose, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa