

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	37	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Modulus at 100% Elongation	0.896	MPa	ASTM D 412
Modulus at 300% Elongation	0.46	MPa	ASTM D 412
Shore A Hardness	30	-	ASTM D 2240
Tear Strength	17.5	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	13	%	ASTM D 395
Tensile Strength at Break	3.31	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
<b>Other properties</b>			
Density	1050	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Mold temperature	15.6 - 26.7	°C	-
Zone 1	160 - 177	°C	-
Zone 2	177 - 188	°C	-
Zone 3	188 - 204	°C	-
Nozzle temperature	188 - 204	°C	-
Screw speed	25 - 75	rpm	-
Injection speed	25.4 - 127	mm/s	-
Back pressure	0.345 - 1.03	MPa	-
Holding pressure	0.689 - 2.41	MPa	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Black

### Features

Anti Slip, Good Adhesion, Soft Feel

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

General Purpose, Sports Equipment

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa