

Dynalloy™ OBC8200-BT50

TPE

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	45	-	ASTM D 2240
Tensile Strength at Break	4.72	MPa	ASTM D 412
Elongation at Break	930	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion, Blow Molding

Features

Soft Feel

Delivery form

Pellets

Certifications

Food contact, Food approval BfR, Food approval FDA 21 CFR

Special Characteristics

Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa