

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 300% Elongation	1.23	MPa	ASTM D 412
Shore A Hardness	30	-	ASTM D 2240
Tear Strength	19.1	kN/m	ASTM D 624
Tensile Strength	4.14	MPa	ASTM D 412
Elongation at Break	755	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1060	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Pipe/Tube Extrusion

### Delivery form

Natural Color

### Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

### Features

Soft Feel

### Chemical Resistance

Ozone Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Automotive

### Regional Availability

North America