

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 300% Elongation	3.08	MPa	ASTM D 412
Shore A Hardness	62	-	ASTM D 2240
Tear Strength	30.6	kN/m	ASTM D 624
Tensile Strength	6.37	MPa	ASTM D 412
Elongation at Break	730	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ASTM D 792

Characteristics

Processing

Pipe/Tube Extrusion

Delivery form

Natural Color

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Soft Feel

Chemical Resistance

Ozone Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Automotive

Regional Availability

North America