

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Modulus at 300% Elongation	<b>6.1</b>	MPa	ASTM D 412
Shore A Hardness	<b>94</b>	-	ASTM D 2240
Tear Strength	<b>45.2</b>	kN/m	ASTM D 624
Tensile Strength	<b>11.1</b>	MPa	ASTM D 412
Elongation at Break	<b>639</b>	%	ASTM D 412

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1180</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Pipe/Tube Extrusion

**Delivery form**

Natural Color

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Features**

Soft Feel

**Chemical Resistance**

Ozone Resistance

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Automotive

**Regional Availability**

North America