

**Product Texts**

TPO/PS Compound

**Processing/Physical Characteristics**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>0.6</b>	%	ISO 294-4, 2577

**Mechanical properties**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>300</b>	MPa	ISO 527
Izod notched impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>N</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-20</b>	°C	-

**Other properties**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>960</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Europe